

PROCESSING INSTRUCTIONS - MAGICUT PUFF



FABRICS

COTTON, POLYESTER,
MIX OF BOTH, ACRYLIC
AND SIMILAR FABRICS



PRESSURE

MEDIUM
/LOW



TEMPERATURE

140°C / 285°F



TIME

PRE PRESS GARMENT - 3 SECONDS
PRESS WHITE/BLACK PUFF - 10 SECONDS



PEEL

WARM



GOLD/SILVER ONLY - TIME

PRESS **GOLD/SILVER** AGAIN FOR 15 SECONDS
WITH RELEASE PAPER FOR PUFF EFFECT



WASHABLE

UP TO 60°C