Fluoropolymer Tubing - PFA

Parker Legris PFA (perfluoroalkoxy) tubing offers 10 times greater durability than other fluoropolymer tubings (PTFE, FEP and PVDF) under severe chemical and mechanical conditions. This tubing range is available in three material grades, offering perfect compatibility with all applications, even in extreme environments.

Product Advantages

Great Versatility

Exceptional chemical inertia

A flexible alternative to stainless steel tubing

Broad range of working temperatures, from cryogenic to extreme heat

Non-stick properties allowing conveyance of many

fluids & gases

Outstanding resistance to ageing

Fluoropolymer with the lowest permeability

Non-flammable

UV-transparent

Tube marking on request

Silicone-free



Three Material Clear High Purity PFA: to cover all applications, including those requiring maximum mechanical resistance

Coloured PFA: for circuit identification

Black Antistatic PFA: eliminates all risk of electrostatic

discharge



Food-Process Fuel Cells Electrical/Electronics Aircraft Oil/Gas Industry Pharmaceutical Medical Chemical Clean Rooms

Technical Characteristics

Compatible Fluids	Medical, bio-compatible, food process, gas, compressed air
Working Pressure	Vacuum to 36 bar
Working Temperature	-196°C to +260°C
Component Materials	Perfluoroalkoxy • High Purity PFA • Translucent coloured PFA • Antistatic PFA

Reliable performance is dependent upon the type of fluid conveyed and fittings being used. Use is guaranteed with a vacuum of 755 mm Hg (99% vacuum).

Regulations

Medical

USP: Class VI (A)

External communication devices

Industrial

UL94 V-0 (Fire resistance)


DI: 2002/95/EC (RoHS), 2011/65/EC DI: 97/23/EC (PED)

RG:1907/2006 (REACH) DI: 94/09/EC (ATEX, black tubing) Food Industry

FDA: 21 CFR 177.1550 (clear, translucent coloured)

RG: 1935/2004 NSF 51 (material)

Performance of PFA Tubing



Tube 0.D.	Tube O.D. Tolerance
4 to 8 mm	+0.10 / -0.10
10 to 12 mm	+0.15 / -0.15

Connected to Parker Legris push-in fittings, the calibration of Parker Legris tubing ensures perfect sealing based on NF E49-100.

To calculate burst pressure, the values in this graph should be multiplied by 3.

Packaging

Tubepacke: 10 m, 50 m, 100 m

1010T...P Fluoropolymer (PFA) Tubing

Tubepack® 10 m

0.D. (mm)	I.D. (mm)	C R	High purity	crystal	crystal	Crystal	kg
4	2	12	1010T04P00	1010T04P12	1010T04P13	1010T04P14	0.087
6	4	34	1010T06P00	1010T06P12	1010T06P13	1010T06P14	0.237
8	6	60	1010T08P00	1010T08P12	1010T08P13	1010T08P14	0.410
10	8	95	1010T10P00	1010T10P12	1010T10P13	1010T10P14	0.723
12	9	120	1010T12P00	1010T12P12	1010T12P13	1010T12P14	1.148

1050T...P Fluoropolymer (PFA) Tubing

Tubepack_® 50 m

0.D. (mm)	I.D. (mm)	€ R	High purity	crystal	crystal	Crystal	kg
4	2	12	1050T04P00	1050T04P12	1050T04P13	1050T04P14	0.435
6	4	34	1050T06P00	1050T06P12	1050T06P13	1050T06P14	1.185
8	6	60	1050T08P00	1050T08P12	1050T08P13	1050T08P14	2.050
10	8	95	1050T10P00	1050T10P12	1050T10P13	1050T10P14	3.615
12	9	120	1050T12P00	1050T12P12	1050T12P13	1050T12P14	5.740

1100T...P Fluoropolymer (PFA) Tubing

Tubepack® 100 m

0.D. (mm)	I.D. (mm)	C R	High purity	crystal	crystal	crystal	kg
4	2	12	1100T04P00	1100T04P12	1100T04P13	1100T04P14	0.870
6	4	34	1100T06P00	1100T06P12	1100T06P13	1100T06P14	2.370
8	6	60	1100T08P00	1100T08P12	1100T08P13	1100T08P14	4.100
10	8	95	1100T10P00	1100T10P12	1100T10P13	1100T10P14	7.230
12	9	120	1100T12P00	1100T12P12	1100T12P13	1100T12P14	11.480

1010T..A Fluoropolymer (PFA) Antistatic Tubing

Tubepack_® 10 m

0.D. (mm)	I.D. (mm)	€ R	<u> </u>	kg
4	2	12	1010T04A01	0.087
6	4	34	1010T06A01	0.237
8	6	60	1010T08A01	0.410
10	8	95	1010T10A01	0.723
12	9	120	1010T12A01	1.148

1050T...A Fluoropolymer (PFA) Antistatic Tubing

Tubepack_® 50 m

0.D. (mm)	I.D. (mm)	€ R	<u> </u>	kg
4	2	12	1050T04A01	0.435
6	4	34	1050T06A01	1.185
8	6	60	1050T08A01	2.050
10	8	95	1050T10A01	0.362
12	9	120	1050T12A01	5.740