

# Declaration of Performance

No. DOP-01-C2-02-T2008 / Page 1 of 4

## C2 Exterior Strong-Fix Premium Screws



Material - Carbon Steel (C1022)

Head Type - Double Countersunk

Screw Diameter (mm) - 4.0, 5.0, 6.0

We hereby declare these designated products have performed initial type testing under system 3, Annex V of the regulation (EU) no. 305/2011 (Construction Products Regulation), with the reference to the harmonised European standard (hEN) BS EN 14592:2008+A1:2012 (Timber structures - Dowel type fasteners - Requirements) for screws intended for the use in "load bearing timber structures" and produced the calculation/test reports as attached;

The initial type testing has been carried out by independent notified body;  
Strojirensky Zkusebni Ustav, NB # 1015, Hudcova 424/56B, 621 00 Brno-Medlánky, Czechia

Certificate Number: CPR-J-00613-22, CPR-J-00615-22 &amp; CPR-J-00616-22

Test Report Number: No. 30-15985/2/JP, No. 30-15985/4/JP &amp; No. 30-15985/5/JP

Factory Process Control (FPC) has been established by the factory.

This declaration is valid until there is a significant change in the product and declared characteristics.  
ie. raw material or change in production process.

This declaration is the responsibility of the importer ; T.I.Midwood & Co. Ltd.

Simon Midwood

Managing Director

TIMCO House  
2022

2022

Name

Position

Signature

Location &amp; Date

Test Year

# Declaration of Performance

No. DOP-01-C2-02-T2008 / Page 2 of 4

## C2 Exterior Strong-Fix Premium Screw Double Countersunk Head - Ø4.0mm

### Material & Geometry

Material	Carbon Steel (C1022)
Screw diameter (mm)	4.0
Head diameter (mm)	7.82
Inner thread diameter (mm)	2.45

### Mechanical Strength & Stiffness

Characteristic yield moment $M_{y,k}$ at 17° [Nmm] (thread section) in acc. to EN 409	3021
Characteristic withdrawal parameter (loading across the fibre) $f_{ax,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1382 with density of wood $\rho_k = 350\text{kg/m}^3$	16.81
Characteristic withdrawal parameter (loading along the fibre) $f_{ax,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1382 with density of wood $\rho_k = 350\text{kg/m}^3$	13.55
Characteristic head pull-through parameter $f_{tens,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1383 with density of wood $\rho_k = 350\text{kg/m}^3$	23.57
Characteristic tensile capacity $f_{tens,k}$ [kN] in acc. to EN 1383	5.57
Characteristic torsional ratio in acc. to EN 15737 with density of wood $\rho_k = 450\text{kg/m}^3$	5.44

### Durability

Coating (Finish)	Silver Organic
Corrosion protection	Service Class 3 acc. to EN 1995-1-1

# Declaration of Performance

No. DOP-01-C2-02-T2008 / Page 3 of 4

## C2 Exterior Strong-Fix Premium Screw Double Countersunk Head - Ø5.0mm

### Material & Geometry

Material	Carbon Steel (C1022)
Screw diameter (mm)	5.0
Head diameter (mm)	9.70
Inner thread diameter (mm)	3.05

### Mechanical Strength & Stiffness

Characteristic yield moment $M_{y,k}$ at 14° [Nmm] (thread section) in acc. to EN 409	6447
Characteristic withdrawal parameter (loading across the fibre) $f_{ax,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1382 with density of wood $\rho_k = 350\text{kg/m}^3$	15.84
Characteristic withdrawal parameter (loading along the fibre) $f_{ax,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1382 with density of wood $\rho_k = 350\text{kg/m}^3$	13.11
Characteristic head pull-through parameter $f_{tens,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1383 with density of wood $\rho_k = 350\text{kg/m}^3$	21.60
Characteristic tensile capacity $f_{tens,k}$ [kN] in acc. to EN 1383	9.63
Characteristic torsional ratio in acc. to EN 15737 with density of wood $\rho_k = 450\text{kg/m}^3$	4.04

### Durability

Coating (Finish)	Silver Organic
Corrosion protection	Service Class 3 acc. to EN 1995-1-1

# Declaration of Performance

No. DOP-01-C2-02-T2008 / Page 4 of 4

## C2 Exterior Strong-Fix Premium Screw Double Countersunk Head - Ø6.0mm

### Material & Geometry

Material	Carbon Steel (C1022)
Screw diameter (mm)	6.0
Head diameter (mm)	11.80
Inner thread diameter (mm)	3.71

### Mechanical Strength & Stiffness

Characteristic yield moment $M_{y,k}$ at 12° [Nmm] (thread section) in acc. to EN 409	10618
Characteristic withdrawal parameter (loading across the fibre) $f_{ax,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1382 with density of wood $\rho_k = 350\text{kg/m}^3$	15.05
Characteristic withdrawal parameter (loading along the fibre) $f_{ax,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1382 with density of wood $\rho_k = 350\text{kg/m}^3$	12.08
Characteristic head pull-through parameter $f_{tens,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1383 with density of wood $\rho_k = 350\text{kg/m}^3$	19.78
Characteristic tensile capacity $f_{tens,k}$ [kN] in acc. to EN 1383	13.32
Characteristic torsional ratio in acc. to EN 15737 with density of wood $\rho_k = 450\text{kg/m}^3$	3.74

### Durability

Coating (Finish)	Silver Organic
Corrosion protection	Service Class 3 acc. to EN 1995-1-1