

Declaration of Performance

No. DOP-01-C2-03-T2008 / Page 1 of 2

C2 Floor-Fix Premium Screws



Material - Carbon Steel (C1022)

Head Type - Countersunk

Screw Diameter (mm) - 4.2

We hereby declare these designated products have performed initial type testing under system 3, Annex V of the regulation (EU) no. 305/2011 (Construction Products Regulation), with the reference to the harmonised European standard (hEN) BS EN 14592:2008+A1:2012 (Timber structures - Dowel type fasteners - Requirements) for screws intended for the use in "load bearing timber structures" and produced the calculation/test reports as attached;

The initial type testing has been carried out by independent notified body;
Strojirensky Zkusebni Ustav, NB # 1015, Hudcova 424/56B, 621 00 Brno-Medlánky, Czechia

Certificate Number: E-30-20339-15

Test Report Number: No. 30-10555

Factory Process Control (FPC) has been established by the factory.

This declaration is valid until there is a significant change in the product and declared characteristics.
ie. raw material or change in production process.

This declaration is the responsibility of the importer ; T.I.Midwood & Co. Ltd.

Simon Midwood

Managing Director

TIMCO House
2015

2015

Name

Position

Signature

Location & Date

Test Year

Declaration of Performance

No. DOP-01-C2-03-T2008 / Page 2 of 2

C2 Floor-Fix Premium Screws Countersunk Head - Ø4.2mm

Material & Geometry

Material	Carbon Steel (C1022)
Screw diameter (mm)	4.2
Head diameter (mm)	8.20
Inner thread diameter (mm)	2.50

Mechanical Strength & Stiffness

Characteristic yield moment $M_{y,k}$ at 16° [Nmm] (thread section) in acc. to EN 409	3930
Characteristic withdrawal parameter (loading across the fibre) $f_{ax,k}$ [N/mm ²] in acc. to EN 1382 with density of wood $\rho_k = 355\text{kg/m}^3$	15.74
Characteristic withdrawal parameter (loading along the fibre) $f_{ax,k}$ [N/mm ²] in acc. to EN 1382 with density of wood $\rho_k = 355\text{kg/m}^3$	12.54
Characteristic head pull-through parameter $f_{tens,k}$ [N/mm ²] in acc. to EN 1383 with density of wood $\rho_k = 440\text{kg/m}^3$	24.18
Characteristic tensile capacity $f_{tens,k}$ [kN] in acc. to EN 1383	6.49
Characteristic torsional ratio in acc. to EN 15737 with density of wood $\rho_k = 450\text{kg/m}^3$	5.23

Durability

Coating (Finish)	Zinc or Yellow
Corrosion protection	Service Class 1 acc. to EN 1995-1-1